

General Description



Breathable transparent polyurethane/urethane/TPU film on paper carrier with a long history of use in medical applications

Typical Property	Typical Value
Elongation at break, MD (%)	700
Thickness (Micron)	36
Weight (g/m ²)	38
MVTR, upright (g/m ² per 24hrs @37°C)	1000
Tensile Strength MD (gf/cm)	750
Tensile Strength TD (gf/cm)	750
Nominal Length at max width (lm)	1000
Minimum Width (mm)	50
Maximum Width (mm)	1300
Carrier	70gsm single sided release paper
Liner	n/a
Adhesive	n/a
Stripping Load (Release) (gf/cm)	1
Elongation at break, TD (%)	700

Product Information revised 7th March 2018

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

SWM INTL

Broad Lane • Gilberdyke • East Yorkshire • HU15 2TD
+44 (0) 1430 440757 • ams@swmintl.com • <http://swm.indicoll.xyz>