

General Description	
RF60C	Transparent scrim reinforced polyurethane/urethane film on paper carrier with a long history of use in medical applications
Typical Property	Typical Value
Thickness (Micron)	110
Weight (g/m <sup>2</sup> )	60
MVTR, upright (g/m <sup>2</sup> per 24hrs @37°C)	900
Tensile Strength MD (gf/cm)	1400
Tensile Strength TD (gf/cm)	900
Nominal Length at max width (lm)	1000
Minimum Width (mm)	50
Maximum Width (mm)	1290
Carrier	100gsm single sided release paper
Liner	n/a
Adhesive	n/a
Other Information	Scrim reinforced
Stripping Load (Release) (gf/cm)	1.3
Elongation at break, MD (%)	50
Elongation at break, TD (%)	30

Product Information revised 7th March 2018

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

**SWM INTL**

Broad Lane • Gilberdyke • East Yorkshire • HU15 2TD  
+44 (0) 1430 440757 • [ams@swmintl.com](mailto:ams@swmintl.com) • <http://swm.indicoll.xyz>