


H514 Yellow



General Description



Typical Property	Typical Value
Thickness (micron)	130
Film Weight (g/m ²)	13.6
Boss Count (MD) (per 25.4mm)	20
Boss Count (TD) (per 25.4mm)	23
Tensile Strength MD (gf/cm)	560
Tensile Strength TD (gf/cm)	440
Nominal Length (lm)	1500
Min Length (lm)	500
Minimum Width (mm)	50
Maximum Width (mm)	1730

Product Information revised 27th April 2015

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

SWM INTL

Broad Lane • Gilberdyke • East Yorkshire • HU15 2TD
+44 (0) 1430 440757 • ams@swmintl.com • <http://swm.indicoll.xyz>